

# PPG Laboratory Test Results Certification

## Kesternich

PPG Industries, Inc. certifies the following performance properties for the DURANAR® Coil Coating Systems when applied and baked on properly cleaned and pretreated substrates, according to PPG specifications:

<b>Coatings:</b>	DURANAR® XL PLUS
<b>Test:</b>	DIN 50018 Kesternich-Practice for Conducting Moist SO2 Test.
<b>Specification:</b>	30 cycles in a properly maintained Kesternich cabinet charged with 2 liters of deionized water and 2 liters sulfur dioxide.
<b>Result:</b>	DURANAR® XL Plus will perform for 30 cycles with no blistering, white rust or loss of adhesion on steel or aluminum. No objectionable color change.

