

# PPG Laboratory Test Results Certification

## Detergent Resistance

PPG Industries, Inc. certifies the following performance properties for the DURANAR® Coil & Extrusion Coating Systems when applied and baked on properly cleaned and pretreated substrates, according to PPG specifications:

<b>Coatings:</b>	DURANAR®
<b>Test:</b>	ASTM D2248 - Detergent Resistance of Organic Finishes
<b>Specification:</b>	Prepare a 3% solution of detergent and distilled water as outlined in ASTM D2248. Immerse at least 2 test specimens in the detergent solution at 100°F for 72 hours. Remove and wipe the sample dry. Immediately apply tape (#610 3M Scotch or equivalent) to the test area and sharply pull off at a right angle to the plane of the surface being tested.
<b>Result:</b>	No loss of adhesion of the film to the metal. No blistering and no significant appearance change when examined by the unaided eye.

