

LACKIERPISTOLENEMPFEHLUNG ANEST IWATA

| PRODUKT | CODE | LS 400 | WS 400 | WS 400 evo clear | W-400 WBX | LS-400 entech | LPH-300 | W-300 WB | LPH-80 | AZ3 HTE2 |
|-----------------------------|--|---|------------------------------|---------------------------|-----------------------|---|-------------------------------|----------------|---|----------------|
| | | SERIE 2 | SERIE 2 | Compliant | | HVLP | Füller | Smart Repair | Spot-Repair | HVLP |
| Polyester Spritzspachtel | A712 | | | | | | | | | 2,5 2,0 bar |
| Wash Primer chromatfrei | D8092 | | | 1,3 HD 2,0 bar | 1,3 2,0 bar | | | | | |
| Epoxy Grundierfüller | D8595 | | | 1,4-1,5 HD 2,0 bar | | | | | | |
| DP4000 2K Primer | D8501/5/7 | | | 1,3-1,4 HD 2,0 bar | 1,4 2,0 bar | | | | | |
| DP5000 2K Primer | D8521/5/7 | | | | | | 1,8 1,0-1,5 bar | | | |
| Rapid-Build Primer | D8541/5/7 | | | | | | 1,6-1,8 1,0-1,5 bar | | | |
| 2K UHS Greymatic Füller | D8018/19/24 | | | | | | 1,6-1,8 1,0-1,5 bar | | | |
| 2K UHS Deltron Progress | D60XX | | 1,2-1,3 HD 2,0 bar | 1,3-1,4 HD 1,8-2,0 bar | 1,3-1,4 2,0 bar | | | | 1,2 1,0-1,2 bar | |
| ENVIROBASE High Performance | T40XX | 1,2-1,3 ETS 1,6-1,8 bar Nebelgang: 1,1-1,3 bar | | | | 1,3 ETS 1,6-1,8 bar Nebelgang: 1,0-1,3 bar | | 1,2 1,5 bar | 1,2 1,0-1,2 bar Nebelgang: 0,8-1,0 bar | |
| 2K HS/UHS Klarlacke | D8135 D8140 D8173 D8175 D8176 D8177 | | 1,2-1,3 HD 2,0 bar | 1,3 HD 1,8-2,0 bar | 1,3-1,4 2,0 bar | | | 1,2 1,5 bar | 1,2 1,0-1,2 bar | |
| 2K HS CeramicClear | D8122 | | 1,2-1,3 HD 2,0 bar | 1,3 HD 2,0 bar | | | | | 1,2 1,0-1,2 bar | |
| 2K Matt-Lacksystem | D8115/17 | 1,3-1,5 ETS 2,0 bar | | | | 1,3-1,5 ETS 1,8 bar | | | 1,2 1,0-1,2 bar | |

* Angaben in **fett/bold**: = primäre Empfehlung



LACKIERPISTOLENEMPFEHLUNG DEVILBISS

| PRODUKT | CODE | GTI Pro | | GTI Pro LITE | | DV1-B | PRI Pro LITE | SRI Pro LITE | |
|-----------------------------|--|---|------------------------|---|--------------------|--|------------------------|---|---|
| | | HVLP HV30 | Transtech TE20 | HVLP LK HV30 | Transtech LK TE20 | HVLP / Plus | Transtech PR10 | HVLP HV5 | Transtech TE5 |
| Polyester Spritzspachtel | A712 | | | | | | 2,5 2,0-2,5 bar | | |
| Wash Primer chromatfrei | D8092 | 1,2-1,3 2,0 bar | 1,3 2,0 bar | | 1,3 2,0 bar | | | | |
| Epoxy Grundierfüller | D8595 | | 1,3-1,6 2,0 bar | | 1,3-1,6 2,0 bar | | | | |
| DP4000 2K Primer | D8501/5/7 | | 1,3-1,4 2,0 bar | | 1,3-1,4 2,0 bar | | | | |
| DP5000 2K Primer | D8521/5/7 | | | | | | 1,6-1,8 2,0-2,5 bar | | |
| Rapid-Build Primer | D8541/5/7 | | | | | | 1,6-1,8 2,0-2,5 bar | | |
| 2K UHS Greymatic Füller | D8018/19/24 | | | | | | 1,6-1,8 2,0-2,5 bar | | |
| 2K UHS Deltron Progress | D60XX | | 1,3-1,4 2,0 bar | | 1,3-1,4 2,0 bar | | | 1,2-1,4 1,0-2,0 bar | 1,2-1,4 1,0-2,0 bar |
| ENVIROBASE High Performance | T40XX | 1,3 1,6-1,8 bar Nebelgang: 1,0-1,3 bar | | 1,3 1,6-1,8 bar Nebelgang: 1,0-1,3 bar | | 1,2B 1,8bar Nebelgang: 1,4bar /Silber grob 1,2bar | | 1,2-1,4 1,0-2,0 bar Nebelgang: 1,0-1,3 bar | 1,2-1,4 1,0-2,0 bar Nebelgang: 1,0-1,3 bar |
| 2K HS/UHS Klarlacke | D8135 D8140 D8173 D8175 D8176 D8177 | | 1,2-1,3 2,3-2,5 bar | | 1,2-1,3 2,0 bar | | | 1,2-1,4 1,0-2,0 bar | 1,2-1,4 1,0-2,0 bar |
| 2K HS CeramicClear | D8122 | | 1,2-1,3 2,3-2,5 bar | | 1,2-1,3 2,0 bar | | | 1,2-1,4 1,0-2,0 bar | 1,2-1,4 1,0-2,0 bar |
| 2K Matt-Lacksystem | D8115/17 | 1,4 1,8 bar | | 1,4 1,8 bar | | | | | |

LACKIERPISTOLENEMPFEHLUNG SATA

| PRODUKT | CODE | SATAjet 5000 B | | SATAjet X 5500 | | SATAmijet 4400 B | | SATAjet 100 BF | |
|-----------------------------|----------------------------------|---|-------------------------|--|---------------------------------|---|------------------------|--------------------|--------------------|
| | | HVLP | RP | HVLP | RP | HVLP | RP | HVLP | RP |
| Polyester Spritzspachtel | A712 | | | | | | | | P 2,0 bar |
| Wash Primer chromatfrei | D8092 | 1,3 2,0 bar | 1,4 2,0-2,2 bar | O Düse 1,3 2,0 bar | I Düse 1,4 2,0-2,2 bar | | | | |
| Epoxy Grundierfüller | D8595 | | 1,3-1,6 1,6-2,0 bar | | I Düse 1,3-1,6 1,6-2,0 bar | | | | |
| DP4000 2K Primer | D8501/5/7 | | 1,2-1,3 2,0-2,2 bar | | I Düse 1,2-1,3 2,0-2,2 bar | | | | |
| DP5000 2K Primer | D8521/5/7 | | | | | | | 1,6-1,8 2,0 bar | 1,6-1,8 2,0 bar |
| Rapid-Build Primer | D8541/5/7 | | | | | | | 1,6-1,8 2,0 bar | 1,6-1,8 2,0 bar |
| 2K UHS Greymatic Füller | D8018/19/24 | | | | | | | 1,6-1,8 2,0 bar | 1,6-1,8 2,0 bar |
| 2K UHS Deltron Progress | D60XX | | 1,2-1,3 2,0-2,2 bar | | I Düse 1,2-1,3 2,0-2,2 bar | | 1,0-1,2 1,0-2,0 bar | | |
| ENVIROBASE High Performance | T40XX | 1,3 1,6-1,8 bar Nebelgang: 1,0-1,3 bar | | O Düse 1,3 1,6-1,8 bar Nebelgang: 1,0-1,3 bar | | 1,2-1,4 1,0-2,0 bar Nebelgang: 1,0-1,3 bar | | | |
| 2K HS/UHS Klarlacke | D8135 D8140 D8173 D8176 | | 1,2 2,0-2,2 bar | | I Düse 1,2 2,0-2,2 bar | | 1,0-1,2 1,0-2,0 bar | | |
| | D8175 D8177 | | 1,1-1,2 2,0-2,2 bar | | I Düse 1,2 2,0-2,2 bar | | 1,0-1,2 1,0-2,0 bar | | |
| 2K HS CeramicClear | D8122 | | 1,2 2,0-2,2 bar | | I Düse 1,2 2,0-2,2 bar | | 1,0-1,2 1,0-2,0 bar | | |
| 2K Matt-Lacksystem | D8115/17 | | 1,3-1,5 1,8 -2,0 bar | | I Düse 1,3-1,5 1,8 - 2,0 bar | | | | |