

PPG Laboratory Test Results Certification

Accelerated Weathering: W-O-M

PPG Industries, Inc. certifies the following performance properties for the DURANAR® Coil & Extrusion Coating Systems when applied and baked on properly cleaned and pretreated substrates, according to PPG specifications:

Coatings:	DURANAR®
Test:	<ul style="list-style-type: none">• ASTM D6695 and ASTM G155 – Standard Practice for Xenon-Arc Exposures of Paint and Related Coatings• ASTM D4214-Degree of Chalking of Exterior Paint Films, Method A-D659• ASTM D2244 -Calculation of Color Difference
Specification:	Coating should withstand a weathering test of 5000 hours in a Xenon-Arc Weather-O-Meter, run in accordance with the above test without cracking, peeling, blistering or loss of adhesion.
Result:	No cracking, peeling, blistering or loss of coating adhesion. Color change is less than 5 delta E color units. Chalk will be no worse than a 8 rating.

