PPG Laboratory Test Results Certification

Dry Film Thickness

PPG Industries, Inc. certifies the following performance properties for the DURANAR® Coil Coating Systems when applied and baked on properly cleaned and pretreated substrates, according to PPG specifications:

Coatings: DURANAR® XL PLUS

Test: • ASTM D7091 - Standard Test Method for Nondestructive

Measurement of Dry Film Thickness of Non-Magnetic

Coatings

Applied to Ferrous Metals & Non-Magnetic Non-

Conductive Coatings

Applied to Non-Ferrous Metals

Specification: Instruments covered by this test method measure coating

thickness by the use of eddy currents. The instrument must be calibrated in accordance with the manufacturer's instructions before using. The instrument probe must be placed directly on the coating surface to take a reading. Three readings are suggested per 3 in. by 6 in. area to

characterize the sample.

Result: The nominal dry film thickness for the DURANAR® XL

Plus system is 0.80 mils each of primer, topcoat and clear coat totaling 2.4 mils. Each coating layer can be specified

at the nominal dry film thickness +/- 0.05 mils.

