

PPG Laboratory Test Results Certification

Accelerated Weathering: W-O-M

PPG Industries, Inc. certifies the following performance properties for the DURANAR® Coil Coating System when applied and baked on properly cleaned and pretreated substrates, according to PPG specifications:

Coatings:	DURANAR PLUS
Test:	<ul style="list-style-type: none">• ASTM D4587 and ASTM G53/G154 - Operating Light - and Water Exposure Apparatus (Fluorescent UV) for Testing Paint and Related Coatings and Materials.• ASTM D4214 - Degree of Chalking of Exterior Paint Films, Method A-D659• ASTM D2244 - Calculation of Color Difference.
Specification:	Coating should withstand a weathering test of 5000 hours in a Fluorescent UV/Condensation Weather-O-Meter, run in accordance with the above test without cracking, peeling, blistering or loss of adhesion.
Result:	No cracking, peeling, blistering or loss of coating adhesion. Color change is less than 5 delta E color units. Chalk will be no worse than a 9 rating.

