



DELTRON[®]NXT

REDUCER SELECTION GUIDE

The below recommendations are only a general reference and should be used solely as a starting point for choosing the appropriate reducer. Your particular spray environment and job size may require slight adjustments.

Temperature

55°F (13°C)	60°F (16°C)	65°F (18°C)	70°F (21°C)	75°F (24°C)	80°F (27°C)	85°F (29°C)	90°F (32°C)	95°F (35°C)	100°F+ (38°C)
DT1565 <i>Primer / Sealer / Basecoat</i>									
		DT1575 <i>Primer / Sealer / Basecoat</i>							
				DT1585 <i>Primer / Sealer / Basecoat</i>					
	DT1565 <i>Clearcoat</i>								
		DT1575 <i>Clearcoat</i>							
				DT1585 <i>Clearcoat</i>					
								DT1595 <i>Primer / Sealer / Basecoat</i>	
									DT1598 <i>Basecoat</i>
							DT1595 <i>Clearcoat</i>		
									DT1598 <i>Clearcoat</i>
Tips: • A higher temp reducer in a clearcoat will allow the surface to stay open longer and provide additional leveling. • Consider the job size when selecting the appropriate reducer. Larger jobs may require a higher temp reducer in order to maintain a “wet” edge. • Where there is excessive air flow in the spray area , a higher temp reducer should be considered to minimize the potential for solvent entrapment.									