

PPG Laboratory Test Results Certification

Kesternich

PPG Industries, Inc. certifies the following performance properties for the DURANAR® Coil Coating System when applied and baked on properly cleaned and pretreated substrates, according to PPG specifications:

Coatings:	DURANAR
Test:	DIN 50018 Kesternich-Practice for Conducting Moist SO ₂ Test.
Specification:	10 cycles in a properly maintained Kesternich cabinet charged with 2 liters of deionized water and 2 liters sulfur dioxide.
Result:	A standard DURANAR® 2-coat will perform for 10 cycles with no blistering, white rust or loss of adhesion on steel or aluminum. No objectionable color change.

