

PPG Laboratory Test Results Certification

Alkali Resistance Sodium Hydroxide

PPG Industries, Inc. certifies the following performance properties for the DURANAR® Coil Coating System when applied and baked on properly cleaned and pretreated substrates, according to PPG specifications:

Coatings:	DURANAR PLUS
Test:	ASTM D1308 - Reagent 6.1.5, Procedure 7.2.
Specification:	A coated panel is subjected to a 10% and 25% sodium hydroxide spot test for a period of 1 hour. The panel is then washed with distilled water, and examined for any effects of significant color change, blisters and overall appearance.
Result:	No effect on coating.

