



PPG LABORATORY TEST RESULTS CERTIFICATION

WET ADHESION

PPG Industries, Inc. certifies the following performance properties for the Duranar® Coil Coating System when applied and baked on properly cleaned and pretreated substrates, according to PPG specifications:

COATING: DURANAR

TEST: ASTM D-870 – Testing Water Resistance of Coatings Using Water Immersion.

SPECIFICATION: A lattice pattern with eleven cuts in each direction (90 degree to each other) is made in the film to the substrate. Immerse the sample in distilled or deionized water at 100 deg. F (38 deg. C) for 24 hours. Remove and wipe the sample dry. Pressure-sensitive #610 3M Scotch tape is applied over the lattice area and then removed rapidly. Test panel should be at ambient temperature.

RESULTS: There shall be no blistering or loss of adhesion of the topcoat to the primer or loss of adhesion of the primer from the pretreated substrate.

Rev. January, 2015